

2021-11

Hazardous metal additives in plastics and their environmental impacts

Turner, Andrew

<http://hdl.handle.net/10026.1/17539>

10.1016/j.envint.2021.106622

Environment International

Elsevier BV

All content in PEARL is protected by copyright law. Author manuscripts are made available in accordance with publisher policies. Please cite only the published version using the details provided on the item record or document. In the absence of an open licence (e.g. Creative Commons), permissions for further reuse of content should be sought from the publisher or author.

Hazardous metal additives in plastics and their environmental impacts

Andrew Turner

School of Geography, Earth and Environmental Sciences, Plymouth University, Drake Circus,
Plymouth PL4 8AA, UK

aturner@plymouth.ac.uk

ORCID: 0000-0003-0505-4561

Montserrat Filella

Department F.-A. Forel, University of Geneva, Boulevard Carl-Vogt 66, CH-1205 Geneva, Switzerland

montserrat.filella@unige.ch

ORCID: 0000-0002-5943-1273

Accepted in Environment International 1 May 2021

<https://doi.org/10.1016/j.envint.2021.106622>

Abstract

Historically, many additives and catalysts used in plastics were based on compounds of toxic metals (and metalloids), like arsenic, cadmium, chromium(VI) and lead. Despite subsequent restrictions, hazardous additives remain in plastics in societal circulation because of the pervasiveness of many products and the more general contamination of recycled goods. However, little is understood about their presence and impacts in the environment, with most studies focusing on the role of plastics in acquiring metals from their surrounding through, for example, adsorption. Accordingly, this paper provides a review of the uses of hazardous, metal-based additives in plastics, the relevant European regulations that have been introduced to restrict or prohibit usage in various sectors, and the likely environmental impacts of hazardous additives once plastics are lost in nature. Examination of the literature reveals widespread occurrence of hazardous metals in environmental plastics, with impacts ranging from contamination of the waste stream to increasing the density and settling rates of material in aquatic systems. A potential concern from an ecotoxicological perspective is the diffusion of metals from the matrix of micro- and nanoplastics under certain physico-chemical conditions, and especially favorable here are the acidic environments encountered in the digestive tract of many animals (birds, fish, mammals) that inadvertently consume plastics. For instance, in vitro studies have shown that the mobilization of Cd and Pb from historical microplastics can greatly exceed concentrations deemed to be safe according to migration limits specified by the current European Toy Safety Directive (17 mg kg⁻¹ and 23 mg kg⁻¹, respectively). When compared with concentrations of metals typically adsorbed to plastics from the environment, the risks from pervasive, historical additives are far more significant.

Keywords: plastics; hazardous additives; metals; regulations; recycling; environmental impacts

1. Introduction

Plastics contain not only polymers or copolymers but chemicals that have been deliberately added for some functionality or that remain as residues or contaminants from the manufacturing process. Functional additives are many and varied include plasticizers, stabilizers, pigments for color, fillers and extenders, flame retardants, blowing agents, antioxidants, impact modifiers, lubricants and antimicrobial agents, while residues include monomers, intermediates and catalysts arising from polymerization and legacy contaminants introduced through material recycling (Murphy, 2001; Hahladakis et al., 2018).

From an environmental perspective, the focus of much recent research has been on the impacts resulting from the mobilization of potentially harmful additives and residues into aqueous media and their subsequent propensity for bioaccumulation. However, the emphasis has been on endocrine-disrupting organic compounds, and in particular phthalate-based plasticizers, bisphenol A, alkylphenols and brominated flame retardants (Engler, 2012; Tanaka et al., 2013; Koelmans et al., 2014; Suhrhoff and Scholz-Böttcher, 2016; De Frond et al., 2019; Schmidt et al., 2019). Significantly, in many recent review and perspective articles where additives are generally discussed, there is little or no mention of chemicals in plastics that contain metals or metalloids known to be harmful (Li et al., 2016; Kwon et al., 2017; Gallo et al., 2018; Franzellitti et al., 2019; Fred-Ahmadu et al., 2020a). This is surprising given the well-established and widespread regulations and restrictions in place for such chemicals in plastics but is perhaps attributable to the misconception that plastics are more significant carriers of adsorbed metals than sources of matrix-bound additive metals (Vedolin et al., 2018; Bradney et al., 2019; Wang et al., 2019; Naqash et al., 2020; Zhang and Chen, 2020).

In the present paper, we describe the historical uses of plastic additives based on metals and metalloids (hereafter collectively referred to as metals) that are deemed to be hazardous; that is, those that have been incorporated into regulations on plastics based on their known or suspected toxicities. Accordingly, we also define relevant, current European regulations for hazardous metals in plastics that are in place for consumer and environmental protection, and discuss shortfalls in these regulations and in circular economies that result in the introduction and dispersion of metals into newer products through material recycling. However, the main focus is a critical evaluation of the role of hazardous metal additives on the environmental behavior and impacts of plastics, including microplastics, that are lost in nature. Here, we also compare concentrations of hazardous metals added to plastics with those acquired from the environment, and make recommendations for risk evaluation based on appropriate European regulations involving metal migration. The intention of this review is that future research will focus on metals and plastics that pose the greatest potential

harm rather than generate results that fail to demonstrate environmental or ecotoxicological significance.

2. Metal additives in plastics

Metals may remain in plastics as catalytic or reaction residues, with a well-documented example being catalytic Sb contaminating polyethylene terephthalate (Takahashi et al., 2008; Filella, 2020). The principal primary source of metals in plastics more generally, however, is functional additives. Metal-based additives may be insoluble inorganic compounds, partially soluble organic compounds or organometallic liquids or salts. Inorganic and organometallic compounds have superior heat resistance and weathering properties and are cheaper, but concerns about their impacts on human health and the environment have resulted in a gradual shift towards organic compounds or non-metal-based alternatives in many sectors (Tolinski, 2015). Metal concentrations in the final product depend on the type of polymer, the nature of the additive and the desired effect (e.g. opacity, depth of shade, thickness of article or intended environment of usage) but can often reach values of several percent on a weight basis (with some inorganic compounds contributing up to one half of the final product mass; Hahladakis et al., 2018).

Metal-based additives have a wide range of functions in plastics and may act as, for example, biocides, antimicrobial agents, lubricants and flame retardants. However, their principal uses are as inert fillers, pigments for color and stabilizers (Murphy, 2001; Janssen et al., 2016). Fillers increase the stiffness and hardness of plastic and often reduce the cost of the product as they are generally cheaper than the base polymer. Industrial mineral fillers include barium sulfate (barytes), calcium carbonate (calcite) and hydrated magnesium silicate (talc). Synthetic organic pigments include phthalocyanines, coordination complexes of copper that mimic the structures of porphyrins, while inorganic pigments include a range of compounds but mainly oxides and sulfides. Some inorganic pigments are multifunctional, with ZnO and Sb₂O₃, for example, both acting as white pigments but also serving as a fungicide and flame retardant synergist, respectively.

As heat stabilizers, metal-based compounds have found extensive use in the versatile, and widely used thermoplastic, polyvinyl chloride (PVC). This material decomposes at a temperature lower than its processing temperature and countering thermo-oxidative degradation requires chemicals that can substitute stable groups for labile chlorine atoms in the polymer and react with HCl generated by the degradation process. To this end, the most important stabilizers are metal soaps, including Pb-, Cd-, Ba-, Ca- and Zn-dicarboxylates, and various organotin compounds (Liu et al., 2007).

Additives are normally mixed with the polymer melt as liquids or solids, with the latter incorporated as fine particles of average diameters on the order of a few micrometers or a few hundred nanometers that disperse in the matrix (Murphy, 2001). Particles larger than this may impact on the strength and appearance of the finished product while smaller particles are subject to agglomeration. Particles are generally prepared by precipitation, calcination (if the compound is sufficiently heat-stable) and grinding. In theory, metal compounds added to plastics as particles, and at least those in inorganic form, should not migrate from the matrix and, therefore, pose little risk to the consumer or, under appropriate disposal conditions, the environment. However, empirical studies undertaken in the 1970s demonstrated the release of insoluble cadmium compounds from micronized particles of acrylonitrile butadiene styrene (ABS), a plastic commonly used in toys, under conditions representative of the human digestive system (Fowles et al., 1977). Concerns about the more general migration of metals that are toxic resulted in regulations and voluntary commitments that restricted the use, concentration or mobility of certain metals in consumer and industrial plastics.

3. Current European regulations on the use of metal additives in plastics and definition of hazardous metals

3.1. European regulations

Table 1 lists metals that are used or that have been used as additives in plastics where European regulatory directives are now in place. Note that many of these directives are adopted or form the basis of regulations in the wider international community (ACCC, 2008; Horn, 2016).

The Toy Safety (TS) Directive and its amendments lay down criteria that toys must meet before being marketed in the EU (European Parliament and Council of the EU, 2009; Council of the European Union, 2017). For materials that can be 'scraped off', including plastics, concentration limits on the migration of eighteen species of sixteen metals in 0.07 M HCl at 37 °C for 2 h are stipulated. In contrast, the Restriction of Hazardous Substances (RoHS) Directive, that includes electronic and electrical plastic housings and insulation (European Parliament and Council, 2003; 2011), and the End-of-Life Vehicles (ELV) Directive, that encompasses plastic components of vehicles (European Parliament and of the Council, 2000; Commission Directive, 2017), set total concentration limits for four metals (1000 mg kg⁻¹ for Cr(VI), Hg and Pb, and 100 mg kg⁻¹ for Cd). The Packaging and Packaging Waste (PPW) Directive is also restricted to these metals but sets a combined total concentration limit of 100 mg kg⁻¹ (European Parliament and Council of the EU, 1994) while the Directive relating to plastics intended to come into contact with foodstuffs (CFS) stipulates different but substantially lower total concentration limits for five metals (Commission Directive, 2002). An

amendment to a Council Directive dealing with the marketing and use of dangerous substances (Council Directive, 1976) now specifically restricts the use of di- and tri-substituted organotin compounds to 1000 mg kg⁻¹ by weight of Sn in plastics, and is particularly relevant to PVC (Commission Decision, 2009).

3.2. Voluntary commitments for PVC

Because of the more specific health and sustainability concerns about the production, use and disposal of PVC, regulations for this particular plastic were called for. However, European producers and stake-holders proposed a series of voluntary measures that included phasing out the intentional introduction of Cd- and Pb-based stabilizers in the EU through a series of charters, like “Vinyl 2010”. Thus, manufacture of Cd used as a stearate or laurate and combined with a Ba ester was discontinued in the EU-27 in 2007, while Pb compounds, including stearates and basic sulfates, were discontinued in the EU-28 in December 2015 and replaced by safer Ca-based alternatives (VinylPlus, 2014). This approach exemplifies how successful voluntary commitments from industry can be without the usual control enforcement from regulatory authorities (Buekens and Sevenster, 2010).

3.3. Hazardous metal additives in plastics

Also identified in Table 1 are metals in plastics that are considered “hazardous”; that is, metals that are currently included in at least two of the aforementioned directives and are defined in the Registration, Evaluation, Authorization and Restriction of Chemicals (REACH) Candidate list of substances of very high concern (SVHC) by the European Chemicals Agency (ECHA). Specific compounds of these metals that have commonly been used in plastics, and in particular in Europe, are defined and characterized in Table 2 along with best estimates of their concentration range in finished products. Note that while most compounds are additives, the list also includes catalysts arising from the manufacturing process that remain in certain plastics.

Organometallic forms of As, Hg and Sn found in plastics include 10,10'-oxybisphenoxarsine, a broad spectrum fungicide and antimicrobial agent used mainly in unplasticized PVC, various phenylmercury compounds used in the production of polyurethane, of which phenylmercury neodecanoate appears to have had the most widespread use in Europe (ECHA, 2010), and dibutyl tins used as stabilizers for PVC when Pb compounds are not suitable or as catalysts in the production of polyurethane. Organic metal compounds (mainly organic acid salts) include the blue pigment, Co(II) diacetate, used for coloring polyethylene terephthalate, and various soaps of Cd used to heat- and light-stabilize PVC. Inorganic compounds include chromium(VI) trioxide, used in the production of polyethylene, various basic salts of Pb used to stabilize and lubricate PVC (note that Pb soaps have had less use in the

European PVC market; ECHA, 2016), and pigments based on compounds of Cd, Hg and Pb (with the latter often employed in combination with Cr(VI)).

Inorganic pigments are centered around the intensely colored, calcined compounds of CdS and PbCrO₄. Cadmium sulfide is bright yellow, with excellent thermal stability, light and weather fastness and chemical resistance. Yellow pigments are achieved with solid solutions of CdS and ZnS while oranges and reds are prepared with solid solutions of CdS and CdSe. Although solid solutions of CdS and HgS can also engender a similar color range (Tamaddon and Hogland, 1993), relatively poor light-fastness and heat stability of the latter sulfide has resulted in limited use of this combination in plastics since the 1950s (Rangos, 2004; Filella and Turner, 2018). Lead chromate is also bright yellow and characterized by high fastness and heat stability, and can be mixed with PbSO₄ and PbMoO₄ (where S and Mo are incorporated into the crystal lattice of the chromate) and, sometimes, PbO, to create a range of colors similar to Cd-based solid solutions. Although chromates are generally applicable in thermoplastics, some polymers require suitable surface treatment of the pigments through, for example, stabilization by silicate or alumina (Ranta-Korpi et al., 2014). Pigments of both Cd and Pb can also be modified or mixed with other pigments to expand the color range to greens and browns.

4. Hazardous metal additives in society and in the environment

4.1. Plastics in societal circulation

In theory, hazardous metal-based additives are no longer intentionally incorporated into contemporary plastics, at least in Europe (Ranta-Korpi et al., 2014). However, recent research suggests that such additives are still illegally employed in certain consumer goods available in the EU (but not necessarily manufactured there) and that historical, industrial plastics containing hazardous metals have been used to manufacture consumer goods with the intention of being environmentally positive (Turner and Filella, 2021). More generally, because of the durability of many plastics, historical products in circulation (like toys) or employed for construction or plumbing (such as PVC window frames and piping) may contain high levels of restricted metals (Turner, 2018b; Turner, 2019; Klöckner et al., 2020; Wagner and Schlummer, 2020). Significantly, Tamaddon and Hogland (1993) suggest that consumer plastics may have lifetimes up to 40 years, a timeframe that significantly predates all regulations given in Table 1. A more recent and detailed product lifetime analysis by Geyer et al. (2017) suggests mean values of 35 years and 20 years for building-construction and industrial-machinery plastics, respectively, with upper estimates exceeding 50 years in both cases.

More broadly, the recycling of plastics, and especially poorly managed or dismantled electronic plastics both within and outside of the EU, has introduced traces of restricted additives into a wider range of contemporary products in both the consumer and industrial sectors (Guzzonato et al., 2017; Turner and Filella, 2017; Eriksen et al., 2018). From a health perspective, this is a particular problem for food-contact plastics or toys designed for young children (Chen et al., 2009; Kuang et al., 2018). Although it has been suggested that plastics known or suspected to contain hazardous additives be recycled into products where human exposure is minimal (e.g. pallets, lumber, refuse facilities, guttering, road signs; Turner, 2018a), identification and sorting of such materials on an industrial scale is not yet feasible.

4.2. Plastics in the environment

In general, the makeup of plastics in the environment reflects that of plastics used by consumers and by industry (neglecting, for now, any chemical modifications incurred by chemical acquisition from the surroundings). However, the plastic stock in the environment is predicted to be more contaminated by restricted additives than the stock in societal circulation, and certainly than in societal plastics manufactured over the past twenty years that reflect the clear decline in the use of hazardous substances (Janssen et al., 2016). This discrepancy may be attributed to a number of factors. Thus, first, plastics have been subject to uncontrolled discharge to the environment since their manufacture began several decades ago, and residence times for terminal or temporary receptors of many products (e.g. sediments and soils) are likely to greatly exceed timeframes of production (Geyer et al., 2017). Second, the historical use of many heavy metal-based additives for thermal and light protection means that such plastics are predicted to be more persistent in the environment relative to plastics that are newer, that contain no additives or that contain additives that degrade. In support of this contention, Prunier et al. (2019) found relatively high concentrations of Ti in plastics sampled from the surface waters of North Atlantic Gyre and proposed that their persistence is related to the UV-absorbing properties of TiO₂. Third, significant point sources of historical and unregulated plastics exist, such as poorly maintained and managed, collapsing coastal landfills (Pope et al., 2012). Fourth, and despite restrictions and regulations in place (see Table 1), many current industrial practices appear to employ plastics that contain hazardous metal-based additives.

These assertions are consistent with high, total or extractable concentrations of restricted metals in many primary objects and secondary fragments of plastic litter on coastal and lacustrine beaches and in freshwater sediment and agricultural fields (Nakashima et al., 2012a; 2012b; Imhof et al., 2016; Turner and Solman, 2016; Turner, 2017; Filella and Turner, 2018, 2021; Munier and Bendell,

2018; Prunier et al., 2019; Santos-Echeandía et al., 2020; Turner et al., 2019). Amongst contaminated litter in these studies are (presumably) historical consumer plastics, including toys, cartridges, bottle tops and compost packaging, fragments of PVC and polyurethane whose origin is usually unknown, and industrial plastics like fragments of fishing line, netting and floats, and polyethylene microbeads (“biobeads”; Turner et al., 2019) used in many modern municipal water treatment plants. Table 3 provides examples of the maximum, total concentrations of Cd and Pb (two of the most widely occurring restricted metals) reported in plastic litter from a range of environments and as determined non-destructively by X-ray fluorescence (XRF) spectrometry or, following sample digestion in nitric acid, by inductively coupled plasma-mass spectrometry. Although the frequency of detection and distribution of concentrations are not always available, the data are entirely consistent with the quantitative information given in Table 2 and serve to illustrate how widespread hazardous additives are in environmental plastics.

Regarding the specific hazardous metals and compounds present in environmental plastics reported in the literature and determined by XRF spectrometry (and exemplified in Figure 1), these are largely in agreement with the information presented in Table 2, but with some significant exceptions and additions. Thus, in many colored objects, Pb is present with Cr and Cd is present alone or with Se or, occasionally, Hg, as inorganic pigments, with Pb and Cd concentrations up to a few thousand mg kg⁻¹ and Pb and Cr usually present in a ratio similar to that in PbCrO₄ (~ 4:1 on a mass basis) (Turner and Solman, 2016; Filella and Turner, 2018). In PVC, Sn or Cd are sometimes present at concentrations of a few thousand mg kg⁻¹ but Pb is more commonly encountered and at concentrations of up to 25,000 mg kg⁻¹ and As is rarely detected (Turner and Solman, 2016; Filella and Turner, 2018). Environmental plastics that are colored black can also contain significant quantities of Pb and, less frequently, Cd. Here, their presence results from the inability to sort dark colored polymers by near infra-red technology and the consequent illegal recycling of black electronic plastics into a wide range of consumer and industrial products (Turner, 2018a; Shaw and Turner, 2019).

5. Potential environmental impacts of hazardous metals in plastics

5.1. Material disposal and recycling

Conventional disposal and energy-from-waste practices involving metal-rich products result in the contamination of landfill leachate, fly ash and bottom ash, with consequent constraints on the use or safe disposal of the latter materials (Mangialardi, 2003; Krausova et al., 2016). In this context, the occurrence or importance of hazardous metals in historical or recycled plastic waste has often been overlooked (Ranti-Korpa et al., 2014). Nakamura et al. (1996) estimated the metal content of component materials in the Japanese municipal and commercial waste stream and suggested that

about 0.5% and 2.4% of total cadmium and lead, respectively, were derived from plastics. In contrast, estimates of metals in the more general, contemporary waste stream suggest that plastic is the main material carrier of total cadmium (almost 50%) and a highly significant carrier of total lead (about 17%) (Vicze et al., 2020). Presumably, the increase in hazardous metal contributions from plastics is attributable to the improved regulation and management of low abundant articles of high metal content, like batteries, paints and electronic equipment, coupled with the pervasiveness of many non-recyclable, historical plastic items. To further significantly reduce the metal content of waste would, therefore, require a means of identifying and eliminating plastics containing hazardous additives that can operate on an industrial scale.

5.2. Density modification

Additives based on heavy metals like Cd and Pb can increase the density of plastic by small but significant amounts. This effect has been employed in the recycling industry in order to separate denser and more harmful additive-laden plastics from “cleaner”, additive-free materials, and in particular for isolating and eliminating plastics enriched in brominated flame retardants (Retegan et al., 2010; Haarman and Gasser, 2016). For polymers whose inherent density is similar to but lower than that of fresh water or seawater ($\rho = 1$ to 1.03 g cm^{-3}), like polyethylene or polypropylene ($\rho \sim 0.90$ to 0.97 g cm^{-3}), a small increase arising from the addition of lead chromate ($\rho = 6.12 \text{ g cm}^{-3}$; Table 2), for example, can result in plastic that sinks rather than floats. While this may be inconsequential for products while in use, in the aquatic environment a small increase in density could markedly modify its transport, fate and bioavailability. To this end, it has been proposed that there may be some kind of fractionation (settling versus floating) of polyolefins in the freshwater and marine environments based on their hazardous metal additive content, and that shore-based sampling of stranded, lighter materials may underestimate the environmental stock of metal-rich plastics (Turner and Filella, 2020).

5.3. Metal diffusion from plastics

Because metal additives are generally not chemically bound to polymers, they have the propensity to mobilize from the matrix via diffusion and mass transfer into the surrounding aqueous phase (Wilson et al., 1982; Mercea et al., 2018; Chen et al., 2019; Mao et al., 2020). This effect is often considered in regulations by fixing a maximum concentration of a chemical allowed to be released when empirical tests are applied. These tests are not based on any mechanistic approach but rather employ simplified and standardized extractant solutions that attempt to mimic realistic conditions, such as those encountered in the human digestive environment (European Parliament and Council of the EU, 2009) or in human sweat (OEKO-TEX Association, 2020; Biver et al., 2021), or those that

simulate the migration of food during storage or cooking (Conti, 2008; van Putten, 2011; Kao, 2012; Schmid and Welle, 2020).

Fluxes of metals in plastics can be theoretically described by Fick's first law provided that diffusion coefficients for the metals and their compounds actually present in the polymers are known (PlasticsEurope, undated; Barnes et al., 2007). Published diffusion coefficients are sparse and often limited to specific problems such as migration into potable water or food (Hampe and Piringner, 1998; Adams et al., 2011; Fang and Vitrac, 2017) but a recent compilation of estimates obtained at or around room temperature and relevant in the context of metal migration from environmental plastics is given by Town et al. (2018). Here, values are $1.5 \times 10^{-20} \text{ m}^2 \text{ s}^{-1}$ for Pb acetate in low density polyethylene, about $10^{-15} \text{ m}^2 \text{ s}^{-1}$ for species of dibutyl tin in polypropylene, 1.7×10^{-17} to $5 \times 10^{-20} \text{ m}^2 \text{ s}^{-1}$ for Cd stearate in PVC, and 6×10^{-17} to $4 \times 10^{-23} \text{ m}^2 \text{ s}^{-1}$ for Pb stearate and dibasic Pb phosphite in PVC. By comparison, diffusion coefficients for metal ions in aqueous media are on the order of 5 to $20 \times 10^{-10} \text{ m}^2 \text{ s}^{-1}$.

The rate at which mobilization by molecular diffusion takes place is proportional to the square of the distance to travel. This means that the complete release of metals or metallic compounds from very small particles or thin sheets (of nanometer to micrometer dimensions) is predicted to take place over timescales of hours to days, and nanoplastics exposed to the environment are predicted to be rapidly depleted of metal additives. On the other hand, the complete metal release from larger particles (hundreds of micrometers to millimeter dimensions) is predicted to take years to decades or longer. In practice, however, studies often reveal that metal release from plastics of this size range is significantly more rapid, with rates of mobilization flattening after a period of time (Martin and Turner, 2019; Smith and Turner, 2020; see Figure 2). This suggests that there may be a pulse of initial metal release, possibly due to the presence of a "leachable" layer at the surface of the plastic, followed by much slower diffusion. Such an effect has recently been invoked to explain the nature and kinetics of Sb release from PET bottles (Filella, 2020).

5.4. Mobilization of metals from plastics in the environment

The rate of metal mobilization from plastic will increase if conditions favor the dissociation of metal compounds in the matrix or alter the speciation in the aqueous phase and maintain or enhance the concentration gradient of the diffusing metal species. Such conditions include a reduction in pH and the introduction of complexants to the aqueous phase, and may be particularly significant in the extracellular (e.g. stomach) or intracellular (e.g. lysosomes) digestive environments of many organisms (Zhong et al., 2006; Smith and Turner, 2020). Some hazardous additives, including cadmium sulfoselenide pigments, are also photoactive and undergo more ready dissociation and

diffusion when exposed to visible and ultraviolet light compared with dark conditions (Fowles et al., 1977; Liu et al., 2017). Consequently, a clear increase in Cd mobilization from microplastics is observed when aqueous suspensions are irradiated by artificial sunlight (Liu et al., 2020). Organotin compounds in PVC exhibit both greater mobilization and photodegradation under visible and ultraviolet light but increasing salinity appears to inhibit these effects (Chen et al., 2019).

More generally, metal mobilization is expected to increase when the plastic is weathered or degraded in the environment, presumably because of the associated increase in porosity and surface area of the aged matrix (Zhang et al., 2018). Experiments performed by Nakashima et al. (2016) on newly purchased PVC fishing floats containing Pb stearate as a stabilizer have provided mechanistic and quantitative insights into the effect of surface damage on metal mobilization into pure water. Thus, release is initially rapid, and in particular during the first 24 h, because of diffusion from the surface layer whose thickness is about 1 μm . This is, presumably, equivalent to the leachable layer referred to above and accounts for about 0.1% of total Pb. Thereafter, mobilization tails off as this layer becomes depleted of Pb but is accelerated when the plastic surface is scarified by sandpaper, simulating erosion when beached, for example, and exposes areas of a new leachable layer.

Figure 2 shows results of timed experiments in which two micronized plastics (PVC piping and polycarbonate-ABS reconstituted from electronic waste and containing added Pb and contaminating Cd, respectively) were exposed to conditions designed to replicate the residence time and chemistries of the digestive system of a seabird (Smith and Turner, 2020). **Note the relatively rapid release of metals in the early stages of the experiments, consistent with the initial pulse and leachable layer described above.** Exposure to neutral saline solution ($0.1 \text{ mol L}^{-1} \text{ NaCl}$) at 40°C results in limited but not insignificant mobilization of Pb and Cd; specifically, the percentage of Pb mobilized from PVC is similar to that reported in pure water by Nakashima et al. (2016). The dissolution of compounded inorganic additives is dramatically increased by reducing the pH of the solution to 2.5 (and in the presence of the digestive enzyme, pepsin), and the further addition of menhaden fish oil, mimicking the presence of a dietary component, increases the dissolution of Pb but decreases the release of Cd, presumably by affecting the integrity of the polymer or acting to block diffusing species, respectively. At the end of the exposures, the maximum Pb and Cd concentrations mobilized were about 1800 mg kg^{-1} and 20 mg kg^{-1} , respectively. Relative to total metal concentrations in the plastics (and as annotated), this represents respective bioaccessibilities of about 9% and over 60%. Clearly, therefore, significant quantities of hazardous metals have the potential to be mobilized from historical and recycled plastics under certain environmental or physiological conditions, and in particular those representative of the acidic digestive system of birds, mammals and fish.

Bioaccessibility is not necessarily equivalent to bioavailability and by itself does not provide evidence that metallic additives in plastics exert toxicity. However, the adverse impacts of certain metals (including Pb and Sn) in PVC on aquatic life have been demonstrated empirically, albeit at environmentally unrealistic plastic concentrations. Thus, Lithner et al. (2012) attributed the leaching of metals (including Sn) from PVC products exposed to deionized water for three days at 50 °C to be responsible for toxicity to *Daphnia magna*. More recently, Boyle et al. (2020) found that exposure of up to 500 mg L⁻¹ of PVC particles (mean diameter = 150 µm) to the larvae of zebrafish (*Danio rerio*) increased expression of metallothionein 2, a metal-binding protein, but no expression changes were observed in biomarkers of estrogenic or organic contaminants. Subsequent leachate analysis revealed that Pb mobilized from the plastic was responsible and that aqueous concentrations reached over 80 µg L⁻¹ over a 24 h period.

5.5. Hazardous metals added during manufacture versus accumulated from the environment

Much recent research into or mention of metals and microplastics in the environment refers to material acting as a vector for the transport and bioaccumulation of ions or complexes acquired from the surrounding environment (Vedolin et al., 2018; Bradney et al., 2019; Li et al., 2020; Ta and Babel, 2020; Purwiyanto et al., 2020; Yu et al., 2020). A compilation of concentrations of acid-extractable Cd and Pb associated with various plastics retrieved directly from aquatic settings (as opposed to being exposed to metals under controlled laboratory conditions) is given in Table 4. Note that direct comparisons are hampered by the use of different extractants by the various authors (no standard protocol exists in the literature; Hildebrand et al., 2020) and that in many cases the metals are likely adsorbed onto or co-precipitated with iron oxy(hydroxides) and organic precipitates and associated with surface-bound detritus rather than being directly adsorbed to the plastic itself. Nevertheless, it is clear that these concentrations are orders of magnitude lower than measured or indicative Cd- and Pb-based additive contents in historical or recycled plastics (Tables 2 and 3) and the concentrations of these additives that are potentially mobile (Figure 2). Significantly, and unlike the case for added metals (e.g. Boyle et al., 2020), there is no evidence that adsorbed metals exert any adverse effects on wildlife at concentrations encountered in the environment.

6. Application of regulations to hazardous metals in environmental plastics

The directives described in Table 1 that apply to new or newly recycled products are now **well-recognized and widely enforced in the EU**. However, the period between production-use and disposal or loss of consumer plastics means that many historical or recycled plastics in the environment are non-compliant with respect to current standards or regulatory limits. More generally, there appear to be important loopholes that enable plastics defined as hazardous in one

sector to be recycled into new (compliant or otherwise) goods in another sector that evade regulation or where regulation is less clear. For instance, electrical and electronic plastic containing concentrations of Cd and Pb in excess of the respective RoHS limits of 100 mg kg⁻¹ and 1000 mg kg⁻¹ appears to be recycled widely into consumer goods (Turner, 2018a; Turner and Filella, 2021) and into industrial plastics that are used in water treatment (Turner et al., 2019).

In order to evaluate the risk of such plastics, the accumulation and ecotoxicological implications of metals need to be addressed through studies of bioavailability (or at least bioaccessibility). Chemical bioavailability is a critical component of the TS Directive, with limits stipulated for various metals that are extractable from articles (including plastic toys) under chemical and physiological conditions representative of an infant's stomach; namely, 100 mg of material of < 6 mm in diameter in 5 mL of 0.07 M HCl for 2 h at 37°C and in the dark (British Standard, 1995). Threshold limits are based on the assumption of ingestion of 8 mg material per day and are shown in Table 1.

Rochman et al. (2013) argued for environmental plastics to be classified as hazardous based on more general physical and chemical characteristics but here we propose that more objective and quantitative criteria are available that relate metal concentrations to existing or modified regulations. For example, the northern fulmar (*Fulmarus glacialis*), an indicator species of plastic pollution according to the Oslo-Paris Convention for the North-East Atlantic (OSPAR, 2008), ingests plastics of size comparable to that stipulated by the TS Directive (Van Frankener et al., 2011) and has a digestive chemistry and physiology that is broadly similar to that of the human stomach (Hilton et al., 2020). Critically, however, non-food items can remain trapped in the proventriculus-gizzard for weeks to months as they are ground down to a size small enough to transit into the gut (Avery-Gomm et al., 2012) and the digestive system may contain, additionally, significant quantities of dietary-derived oils (Tanaka et al., 2015). Assuming that the size of plastic particles ingested or ground down in the gizzard are similar to those mechanically micronized as part of British Standard (1995), and assuming that *F. glacialis* ingests an average of 8 mg of plastic per day, one could argue that the current TS Directive limits for metals are applicable for an extended digestive test conducted in the presence of fish oil. The results shown in Figure 2 for acidified saline solution in the presence of fish oil essentially reflect the kinetics of Cd and Pb release from plastics subject to this digestive process. Thus, concentrations of Pb mobilized from PVC in Figure 2 exceed the toy safety limit of 23 mg kg⁻¹ by one or two orders of magnitude throughout the time course while the concentration of Cd mobilized from PC-ABS marginally exceeds the limit of 17 mg kg⁻¹ at the termination of the experiment.

Although historical or recycled plastics clearly pose a risk to wildlife whose digestive chemistry favors the mobilization of hazardous metals, information on the abundance and availability of contaminated plastics in the environment is also required. To this end, two recent studies have provided a valuable insight into the prevalence of Cd and Pb in beached plastic litter (summarized in Table 4). Thus, first, analysis of polyolefin-based microplastic pellets and fragments (< 5 mm) collected from the strandlines of coastal beaches in southwest England by Massos and Turner (2017) revealed that over 100 out of 924 samples contained total Cd or Pb (or both) above the respective TS Directive limits. Second, analysis of a wider range of plastics collected from the shores of Lake Geneva by Filella and Turner (2018) revealed that over 200 out of 678 plastics contained total Cd or Pb (or both) above the respective limits. It would appear, therefore, that between about 10 and 30% of environmental plastics that are beached are potentially harmful with regard to a modified toy safety test. Concentrations of Cd and Pb reported by Prunier et al. (2019) for a more limited number of meso- and microplastics in the North Atlantic gyre (summarized in Table 4) suggests that a similar degree of “non-compliance” may also exist in the open ocean.

In addition to the abundance of contaminated plastics, exposure and risk may also be modified by the selection or avoidance of plastics based on color that is, for example, similar or dissimilar to natural prey (Ory et al., 2017; Duncan et al., 2019). Specifically, and as discussed above, cadmium sulfide and lead chromate and their derivatives are bright yellow, red or orange, while an array of metals are encountered in recycled electronic plastics that tend to be black (Turner, 2018a; Shaw and Turner, 2019).

7. Conclusions

Hazardous metal additives have served various functions in historical plastics (mainly as pigments for color and stabilizers in PVC) but are now restricted under a number of consumer and sustainability regulations. Despite these regulations and the consequent development of safer alternative additives, however, hazardous metals have become dispersed amongst contemporary consumer goods through material recycling. Moreover, because of the pervasiveness of plastics, poor management and disposal of historical plastics and the apparent recent use of restricted additives in marine and industrial applications, hazardous metals widely contaminate plastics lost in nature. Unfortunately, relatively little attention has been paid to hazardous metals in environmental plastics, with the main focus (and misconception) in this setting related to the importance of relatively low concentrations of metals acquired (e.g. adsorbed) from the surroundings. Concentrations of additive-bound metals that can be mobilized from historical plastics under conditions that simulate the digestive environment can be orders of magnitude higher than metal concentrations adsorbed to plastics. Accordingly, it is proposed that the risks posed by these plastics

468 to wildlife could be evaluated by comparing empirically-derived mobilized concentrations with
469 corresponding migration safety limits defined for hazardous metals in consumer products like toys.

470

471 **Declaration of interest statement**

472 The authors declare that they have no conflicts of interest.

473

474

References

- ACCC, 2008. Proposed consumer product safety standard: Limits on migration of lead and certain elements in children's toys. Product Safety Policy Section, Australian Competition & Consumer Commission
- Adams, W.A., Xu, Y., Little, J.C., Fristachi, A.F., Rice, G.E., Impellitteri, C.A., 2011. Predicting the migration rate of dialkylorganotin from PVC pipe into water. *Environmental Science and Technology* 45, 6902-6907.
- Ashton, K., Holmes, L., Turner, A., 2010. Association of metals with plastic production pellets in the marine environment. *Marine Pollution Bulletin* 60, 2050–2055.
- Avery-Gomm, S., O'Hara, P.D., Kleine, L., Bowes, V., Wilson, L.K., Barry, K.L., 2012. Northern fulmars as biological monitors of trends of plastic pollution in the eastern North Pacific. *Marine Pollution Bulletin* 64, 1776-1781.
- Barnes, K.A., Sinclair, C.R., Watson, D.H., (eds) 2007. *Chemical Migration and Food Contact Materials*. Woodhead Publishing, Cambridge, UK.
- Biver, M., Turner, A., Filella, M., 2021. Antimony release from polyester textiles by artificial sweat solutions: A call for a standardized procedure. *Regulatory Toxicology and Pharmacology* 119, 104824.
- Boyle, D., Catarino, A.I., Clark, N.J., Henry, T.B., 2020. Polyvinyl chloride (PVC) plastic fragments release Pb additives that are bioavailable in zebrafish. *Environmental Pollution* 263, 114422.
- Bradney, L., Wijesekara, H., Palansooriya, K.N., Obadamudalige, N., Bolan, N.S., Ok, Y.S., Rinklebe, J., Kim, K.H., Kirkham, M.B., 2019. Particulate plastics as a vector for toxic trace-element uptake by aquatic and terrestrial organisms and human health risk. *Environment International* 131, 104937.
- British Standard, 1995. Safety of Toys – Part 3: Migration of certain elements. BS EN 71-3. BSI, London.
- Buekens, A., Sevenster, A., 2010. Vinyl 2010 – nearing the target date. *Journal of Material Cycles and Waste Management* 12, 184-192.
- Carbery, M., MacFarlane, G.R., O'Connor, W., Afrose, S., Tayloer, H., Palanisami, T., 2020. Baseline analysis of metal(loid)s on microplastics collected from the Australian shoreline using citizen science. *Marine Pollution Bulletin* 152, 110914.
- ChemicalBook CAS DataBase <https://www.chemicalbook.com/ChemicalProductProperty>
- Chen, C., Chen, L., Yao, Y., Artigas, F., Huang, Q., Zhang, W., 2019. Organotin release from polyvinyl chloride microplastics and concurrent photodegradation in water: Impacts from salinity, dissolved organic matter, and light exposure. *Environmental Science and Technology* 53, 10741-10752.
- Chen, S.-J., Ma, Y.-J., Wang, J., Chen, D., Luo, X.-J., Mai, B.-X., 2009. Brominated flame retardants in children's toys: Concentration, composition, and children's exposure and risk assessment. *Environmental Science and Technology* 43, 4200-4206.
- Commission Decision, 2009. Directive 2009/425/EC amending Council Directive 76/769/EEC as regards restrictions on the marketing and use of organostannic compounds for the purpose of adapting its Annex I to technical progress. *Official Journal of the European Union* L138/11.

514 Commission Delegated Directive, 2015. EU Directive 2015/863 amending Annex II to Directive
515 2011/65/EU of the European Parliament and of the Council as regards the list of restricted
516 substances. Official Journal of the European Union L137/10.

517 Commission Directive, 2002. EC Directive 2002/72/EC of 6 August 2002 relating to plastic materials
518 and articles intended to come into contact with foodstuffs. Official Journal of the European
519 Communities L220/18.

520 Commission Directive, 2017. EU Directive 2017/2096 amending Annex II to Directive 2000/53/EC of
521 the European Parliament and of the Council on end-of-life vehicles. Official Journal of the European
522 Union L299/24.

523 Conti, M.E., 2008. Heavy metals in food packaging: The state of the art. Intergovernmental Forum on
524 Chemical Safety Global Partnerships for Chemical Safety.

525 Council Directive, 1976. Directive 76/769/EEC of 27 July 1976 on the approximation of the laws,
526 regulations and administrative provisions of the Member States relating to restrictions on the
527 marketing and use of certain dangerous substances and preparations. Official Journal of the
528 European Communities L262/201.

529 Council of the European Union, 2017. Council Directive (EU) 2017/738 of 27 March 2017 amending,
530 for the purpose of adapting to technical progress, Annex II to Directive 2009/48/EC of the European
531 Parliament and of the Council on the safety of toys, as regards lead. Official Journal of the European
532 Union L110/6.

533 De Frond, H.L., van Seville, E., Parnis, J.M., Diamond, M.L., Mallos, N., Kingsbury, T., Rochman, C.M.,
534 2019. Estimating the mass of chemicals associate with ocean plastic pollution to inform mitigation
535 efforts. Integrated Environmental Assessment and Management 15, 596-606.

536 Duncan, E.M., Arrowsmith, J.A., Bain, C.E., Bowdery, H., Broderick, A.C., Chalmers, T., Fuller, W.J.,
537 Galloway, T.S., Lee, J.H., Lindeque, P.K., Omeyer, L.C.M., Snape, R.T.E., Godley, B.J., 2019. Diet-
538 related selectivity of macroplastic ingestion in green turtles (*Chelonia mydas*) in the eastern
539 Mediterranean. Scientific Reports 9, 11581.

540 ECHA, 2009. Member State Committee Support Document for Identification of Lead Chromate
541 Molybdate Sulfate Red (CI Pigment Red 104) as a Substance of Very High Concern Because of its
542 CMR Properties. European Chemicals Agency, Helsinki.

543 ECHA, 2010. Annex XV Restriction Report Proposal for a Restriction (Phenylmercury Compounds).
544 European Chemicals Agency, Helsinki.

545 ECHA, 2011. Background document to the Opinions on the Annex XV dossier proposing restrictions
546 on five phenylmercury compounds. European Chemicals Agency, Helsinki.

547 ECHA, 2012. Member State Committee Support Document for Identification of Trilead
548 Bis(Carbonate) Dihydroxide [Basic Lead Carbonate] as a Substance of Very High Concern Because of
549 its CMR Properties. European Chemicals Agency, Helsinki.

550 ECHA, 2016. Annex XV Restriction Report. Proposal for a Restriction: Lead compounds-PVC.
551 European Chemicals Agency, Helsinki.

552 ECHA, 2017. Study Report on the Conditions of Use of Five Cobalt Salts: Final report. European
553 Chemicals Agency, Helsinki.

Engler, R.E., 2012. The complex interaction between marine debris and toxic chemicals in the ocean. *Environmental Science and Technology* 46, 12302-13215.

Eriksen, M.K., Pivnenko, K., Olsson, M.E., Astrup, T.F., 2018. Contamination in plastic recycling: Influence of metals on the quality of reprocessed plastic. *Waste Management* 79, 595-606.

European Parliament and Council, 2003. Directive 2002/95/EC of 27 January 2003 on the restriction of the use of certain hazardous substances in electrical and electronic equipment. *Official Journal of the European Union* L37/19.

European Parliament and Council, 2011. Directive 2011/65/EU on the restriction of the use of certain hazardous substances in electrical and electronic equipment (recast). *Official Journal of the European Union* L174/88.

European Parliament and Council of the EU, 1994. Directive 94/62/EC of 20 December 1994 on packaging and packaging waste. *Official Journal of the European Union* L365.

European Parliament and Council of the EU, 2009. Directive 2009/48/EC of the European Parliament and of the Council of 18 June 2009 on the safety of toys. *Official Journal of the European Union* L170/1.

European Parliament and of the Council, 2000. Directive 2000/53/EC of 18 September 2000 on end-of-life vehicles. *Official Journal of the European Communities* L269/34.

Fang, X., Vitrac, O., 2017. Predicting diffusion coefficients of chemicals in and through packaging materials. *Critical Reviews in Food Science and Nutrition* 57, 275-312.

Filella, M., 2020. Antimony and PET bottles: Checking facts. *Chemosphere* 261, 127732.

Filella, M., Turner, A., 2018. Observational study unveils the extensive presence of hazardous elements in beached plastics from Lake Geneva. *Frontiers in Environmental Science* 6, 1 doi:10.3389/fenvs.2018.00001.

Fowles, G.W.A., 1977. The leaching of cadmium from plastic toys. *Science of the Total Environment* 7, 207-216.

Franzellitti, S., Canesi, L., Auguste, M., Wathsala, R.H.G.R., Fabbri, E., 2019. Microplastic exposure and effects in aquatic organisms: A physiological perspective. *Environmental Toxicology and Pharmacology* 68, 37-51.

Fred-Ahmadu, O.H., Ayejuyo, O.O., Benson, N.U., 2020a. Dataset on microplastics and associated trace metals and phthalate esters in sandy beaches of tropical Atlantic ecosystems, Nigeria. *Data in Brief* 31, 105755.

Fred-Ahmadu, O.H., Bhagwat, G., Oluyoye, I., Benson, N.U., Ayejuyo, O.O., Palanisami, T., 2020b. Interaction of chemical contaminants with microplastics: Principles and perspectives. *Science of the Total Environment* 706, 135978.

Gallo, F., Fossi, C., Weber, R., Santillo, D., Sousa, J., Ingram, I., Nadal, A., Romano, D., 2018. Marine litter plastics and microplastics and their toxic chemicals components: the need for urgent preventive measures. *Environmental Sciences Europe* 30, 13.

Geyer, R., Jambeck, J.R., Law, K.L., 2017. Production, use, and fate of all plastics ever made. *Science Advances* 3, e1700782.

593 Guzzonato, A., Puype, F., Harrad, S.J., 2017. Evidence of bad recycling practices: BFRs in children's
594 toys and food-contact articles. *Environmental Science: Processes and Impacts* 19, 956-963.

595 Haarman, A., Gasser, M., 2016. Managing hazardous additives in WEEE plastic from the Indian
596 informal sector. A study on applicable identification & separation methods. *Sustainable Recycling*
597 *Industries*, St. Gallen, Switzerland, 66pp.

598 Hahladakis, J.N., Velis, C.A., Weber, R., Iacovidou, E., Purnell, P., 2018. An overview of chemical
599 additives present in plastics: Migration, release, fate and environmental impact during their use,
600 disposal and recycling. *Journal of Hazardous Materials* 344, 179-199.

601 Hampe, D., Piringer, O., 1998. Studies on the permeation of inorganic salts through plastic films.
602 *Food Additives and Contaminants* 15, 209-216.

603 Hansen, E., Nilsson, N.H., Lithner, D., Lassen, C., 2013. Hazardous substances in plastic materials.
604 COWI and Danish Technological Institute, Vejle, Denmark.

605 Haynes, W.M., (ed), 2015. *CRC Handbook of Chemistry and Physics*, 95th edition. CRC Press, Boca
606 Raton, FL.

607 Hildebrand, L., von der Au, M., Zimmermann, T., Reese, A., Ludwig, J., Pröfrock, D., 2020. A
608 metrologically traceable protocol for the quantification of trace metals in different types of
609 microplastic. *PLoS ONE* 15(7), e0236120.

610 Hilton, G.M., Furness, R.W., Houston, D.C., 2000. A comparative study of digestion in North Atlantic
611 seabirds. *Journal of Avian Biology* 31, 36-46.

612 Horn, D.A., 2016. The international development of RoHS: An analysis of the RoHS regulations
613 worldwide. *IEEE Conference on Technologies for Sustainability SusTech*. IEEE, New York

614 Imhof, H.K., Laforsch, C., Wiesheu, A.C., Schmid, J., Anger, P.M., Niessner, R., Ivleva, N.P., 2016.
615 Pigments and plastic in limnetic ecosystems: A qualitative and quantitative study on microparticles
616 of different size classes. *Water Research* 98, 64-74.

617 Janssen, M.P.M., Spijker, J., Lijzen, J.P.A., Wesselink, L.G., 2016. *Plastics That Contain Hazardous*
618 *Substances: Recycle or Incinerate?* Dutch National Institute for Public Health and the Environment,
619 RIVM, Bilthoven, The Netherlands.

620 Jasna, M.L., Jelena, L., Pero, T., Dubravka, B.V., Jasna, S., Joško, P., 2019. Levels of trace metals on
621 microplastic particles in beach sediments of the island of Vis, Adriatic Sea, Croatia. *Marine Pollution*
622 *Bulletin* 137, 231-236.

623 Kao, Y.M., 2012. A review on safety inspection and research of plastic food packaging materials in
624 Taiwan. *Journal of Food and Drug Analysis* 20, 734-743.

625 Klöckner, P., Reemtsma, T., Wagner, S., 2020. The diverse metal composition of plastic items and its
626 implications. *Science of the Total Environment*, article no. 142870.

627 Koelmans, A.A., Besseling, E., Foekema, E.M., 2014. Leaching of plastic additives to marine
628 organisms. *Environmental Pollution* 187, 49-54.

629 Krausova, K., Gautron, L., Karnis, A., Catillon, G., Borensztajn, S., 2016. Glass ceramics and mineral
630 materials for the immobilization of lead and cadmium. *Ceramic International* 42, 8779-8788.

631 Kuang, J., Abdallah, M.A.-E., Harrad, S., 2018. Brominated flame retardants in black plastic kitchen
 632 utensils: concentrations and human exposure implications. *Science of the Total Environment* 610-
 633 611, 1138-1146.

634 Kwon, J.-H., Chang, S., Hong, S.H., Shim, W.J., 2017. Microplastics as a vector of hydrophobic
 635 contaminants: Importance of hydrophobic additives. *Integrated Environmental Assessment and*
 636 *Management* 13, 494-499.

637 Li, W.C., Tse, H.F., Fok, L., 2016. Plastic waste in the marine environment: A review of sources,
 638 occurrence and effects. *Science of the Total Environment* 566-567, 333-349.

639 Li, W., Lo, H.S., Wong, H.M., Zhou, M., Wong, C.Y., Tam, N.F.Y., Cheung, S.G., 2020. Heavy metals
 640 contamination of sedimentary microplastics in Hong Kong. *Marine Pollution Bulletin* 153, 110977.

641 Lithner, D., Nordensvan, I., Dave, G., 2012. Comparative acute toxicity of leachates from plastic
 642 products made of polypropylene, polyethylene, PVC, acrylonitrile–butadiene–styrene, and epoxy to
 643 *Daphnia magna*. *Environmental Science and Pollution Research* 19, 1763-1772.

644 Liu, H., Gao, H., Long, M., Fu, H., Alvarez, P.J.J., Li, Q., Zheng, S., Qu, X., Zhu, D., 2017. Sunlight
 645 promotes fast release of hazardous cadmium from widely-used commercial cadmium pigments.
 646 *Environmental Science and Technology* 51, 6877-6886.

647 Liu, H., Liu, K., Fu, H., Ji, R., Qu, X., 2020. Sunlight mediated cadmium release from colored
 648 microplastics containing cadmium pigment in aqueous phase. *Environmental Pollution* 263, 114484.

649 Liu, Y.B., Liu, W.Q., Hou, M.H., 2007. Metal dicarboxylates as thermal stabilizers for PVC. *Polymer*
 650 *Degradation and Stability* 92, 1565-1571.

651 Lofrano, G., Nikolaou, A., Libralato, G., Carotenuto, M., 2018. Organotin compounds in marine
 652 sediment: Detection and concerns. *Global NEST Journal*, 20, 128-135.

653 Malik, W.U., Jain, A.K., 1969. Solubility of cadmium laurate using radioactive ^{115m}cadmium as a
 654 tracer. *Journal of Colloid and Interface Science* 31, 460-463.

655 Mangialardi, T., 2003. Disposal of MSWI fly ash through a combined washing-immobilization process.
 656 *Journal of Hazardous Materials* 98, 225-240.

657 Mao, S.H., Gu, W.H., Bai, J.F., Dong, B., Huang, Q., Zhao, J., Zhuang, X.N., Zhang, C.L., Yuan, W.Y.,
 658 Wang, J.W., 2020. Migration of heavy metal in electronic waste plastics during simulated recycling
 659 on a laboratory scale. *Chemosphere* 245, 125645.

660 Martin, K., Turner, A., 2019. Mobilization and bioaccessibility of cadmium in coastal sediment
 661 contaminated by microplastics. *Marine Pollution Bulletin* 146, 940-944.

662 Martins, I., Rodriguez, Y., Pham, C.K., 2020. Trace elements in microplastics stranded on beaches of
 663 remote islands in the NE Atlantic. *Marine Pollution Bulletin* 156, 111270.

664 Massos, A., Turner, A., 2017. Cadmium, lead and bromine in beached microplastics. *Environmental*
 665 *Pollution* 227, 139-145.

666 Mercia, P.V., Losher, C., Petrasch, M., Tosa, V., 2018. Migration of stabilizers and plasticizer from
 667 recycled polyvinylchloride. *Journal of Vinyl and Additive Technology* 24, doi:10.1002/vnl.21609

668 Munier, B., Bendell, L.I., 2018. Macro and micro plastics sorb and desorb metals and act as a point
669 source of trace metals to coastal ecosystems. PLoS ONE 13, e0191759.
670 doi:10.1371/journal.pone.0191759

671 Murphy, J., 2001. Additives for Plastics Handbook, second edition. Elsevier, Amsterdam.

672 Nakamura, K., Kinoshita, S., Takatsuki, H., 1996. The origin and behavior of lead, cadmium and
673 antimony in MSW incinerator. Waste Management 16, 509-517.

674 Nakashima, E., Isobe, A., Kako, S., Itai, T., Takahashi, S., 2012a. Toxic metals derived from plastic
675 litter on a beach. In: Interdisciplinary Studies on Environmental Chemistry, ed. M. Kawaguchi, H.
676 Misaki, T. Sato, T. Yokokawa, T. Itai, T.M. Nguyen, J. Ono, S. Tanabe. Terrapub, pp321-328.

677 Nakashima, E., Isobe, A., Kako, S., Itai, T., Takahashi, S., 2012b. Quantification of toxic metals derived
678 from macroplastic litter on Ookushi beach, Japan. Environmental Science and Technology 46, 10099-
679 10105.

680 Nakashima, E., Isobe, A., Kako, S., Itai, T., Takahashi, S., Gou, X., 2016. The potential of oceanic
681 transport and onshore leaching of additive-derived lead by marine macro-plastic debris. Marine
682 Pollution Bulletin 107, 333-339.

683 Naqash, N., Prakash, S., Kapoor, D., Singh, R., 2020. Interaction of freshwater microplastics with
684 biota and heavy metals: a review. Environmental Chemistry Letters 18, 1813-1824.

685 OEKO-TEX Association, 2020. STANDARD 100 by OEKO-TEX®. [https://www.oeko-](https://www.oeko-tex.com/importedmedia/downloadfiles/STANDARD_100_by_OEKO-TEX_R-ko.pdf)
686 [tex.com/importedmedia/downloadfiles/STANDARD_100_by_OEKO-TEX_R-ko.pdf](https://www.oeko-tex.com/importedmedia/downloadfiles/STANDARD_100_by_OEKO-TEX_R-ko.pdf); Accessed
687 November 2020.

688 Ory, N. C., Sobral, P., Ferreira, J. L., Thiel, M., 2017. Amberstripe scad *decapterus muroadsi*
689 (Carangidae) fish ingest blue microplastics resembling their copepod prey along the coast of Rapa
690 Nui (Easter Island) in the South Pacific subtropical gyre. Science of the Total Environment 586,
691 430-437.

692 OSPAR, 2008. Background document for the EcoQO on plastic particles in stomachs of seabirds.
693 London, 355/2007.

694 Piver, W.T., 1973. Organotin compounds: Industrial applications and biological investigation.
695 Environmental Health Perspectives 4, 61-79.

696 PlasticsEurope, undated. Applicability of mathematical modelling for the estimation of specific
697 migration of substances from plastics. PlasticsEurope AISBL, Brussels.

698 Pope, N.D., O'Hara, S.C.M., Imamura, M., Hutchinson, T.H., Langston, W.J., 2011. Influence of a
699 collapsed coastal landfill on metal levels in sediments and biota – a portent for the future? Journal of
700 Environmental Monitoring 13, 1961-1974.

701 Prunier, J., Maurice, L., Perez, E., Gigault, J., Wickmann, A.C.P., Davranche, M., ter Halle, A., 2019.
702 Trace metals in polyethylene debris from the North Atlantic subtropical gyre. Environmental
703 Pollution 245, 371-379.

704 Purwiyanto, A.I.S., Suteja, Y., Trisno, Ningrum, P.S., Putri, W.A.E., Rozirwan; Agustriani, F; Fauziyah;
705 Cordova, M.R., Koropitan, A.F., 2020. Concentration and adsorption of Pb and Cu in microplastics:
706 Case study in aquatic environment. Marine Pollution Bulletin 158, 111380.

707 Rangos, G., 2004. Inorganic colored pigments, in *Coloring of Plastics: Fundamentals*, 2nd Edn, ed R.
708 A. Charvat. John Wiley, Hoboken, NJ, pp127–145.

709 Ranta-Korpi, M., Vainikka, P., Konttinen, J., Saarimaa, A., Rodriguez, M., 2014. Ash Forming Elements
710 in Plastics and Rubbers. VTT Technical Research Centre of Finland, Espoo, Finland.

711 Retegan, T., Felix, J., Schyllander, J., 2010. Recycling of WEEE Plastics Containing Brominated Flame
712 Retardants - A Swedish perspective Report to the Swedish Environmental Protection Agency.

713 Rochman, C.M., Browne, M.A., Halpern, B.S., et al., 2013. Classify plastic waste as hazardous. *Nature*
714 494, 169-171.

715 RPA, 2005. Risk Assessment Studies on Targeted Consumer Applications of Certain Organotin
716 Compounds. Risk and Policy Analysts Limited, Norfolk, UK.

717 Santos-Echeandía, J., Rivera-Hernández, J.R., Rodrigues, J.P., Moltó, V., 2020. Interaction of mercury
718 with beached plastics with special attention to zonation, degradation status and polymer type.
719 *Marine Chemistry* 222, 103788.

720 Schmid, P., Welle, F., 2020. Chemical migration from beverage packaging materials – A review.
721 *Beverages* 6, 37. doi:10.3390/beverages6020037.

722 Schmidt, N., Fauvelle, V., Ody, A., Castro-Jimenez, J., Jouanno, J., Changeux, T., Thibault, T., Sempere,
723 R., 2019. The Amazon River: A major source of organic plastic additives to the tropical North
724 Atlantic? *Environmental Science and Technology* 53, 7513-7521.

725 Shaw, E.J., Turner, E., 2019. Recycled electronic plastic and marine litter. *Science of the Total*
726 *Environment* 694, 133644.

727 Smith, E.C., Turner, A., 2020. Mobilization kinetics of Br, Cd, Cr, Hg, Pb and Sb in microplastics
728 exposed to simulated, dietary-adapted digestive conditions of seabirds. *Science of the Total*
729 *Environment* 733, 138802.

730 Suhrhoff, T.J., Scholz-Böttcher, B.M., 2016. Qualitative impact of salinity, UV radiation and
731 turbulence on leaching of organic plastic additives from four common plastics — A lab experiment.
732 *Marine Pollution Bulletin* 102, 84-94.

733 Suman, T.Y., Li, W.G., Alif, S., Faris, V.R.P., Amarnath, D.J., Ma, J.G., Pei, D.S., 2020. Characterization
734 of petroleum-based plastics and their absorbed trace metals from the sediments of the Marina
735 Beach in Chennai, India. *Environmental Sciences Europe* 32, 110.

736 Ta, A.T., Babel, S., 2020. Microplastic contamination on the lower Chao Phraya: Abundance,
737 characteristic and interaction with heavy metals. *Chemosphere* 257, 127234.

738 Takahashi, Y., Sakuma, K., Itai, T., Zheng, G., Mitsunobi, S., 2008. Speciation of antimony in PET
739 bottles produced in Japan and China by X-ray absorption fine structure spectroscopy. *Environmental*
740 *Science and Technology* 42, 9045-9050.

741 Tamaddon, F., Hogland, W., 1993. Review of cadmium in plastic waste in Sweden. *Waste*
742 *Management and Research* 11, 287-295.

743 Tanaka, K., Takada, H., Yamashita, R., Mizukawa, K., Fukuwaka, M.-a., Watanuki, Y., 2013.
744 Accumulation of plastic-derived chemicals in tissues of seabirds ingesting marine plastics. *Marine*
745 *Pollution Bulletin* 69, 219-222.

746 Tanaka, K., Takada, H., Yamashita, R., Mizukawa, K., Fukuwaka, M.A., Watanuki, Y., 2015. Facilitated
747 leaching of additive-derived PBDEs from plastic by seabirds' stomach oil and accumulation in tissues.
748 Environmental Science and Technology 49, 11799-11807.

749 Tolinski, M., 2015. Additives for Polyolefins (Second Edition). Elsevier, Amsterdam.

750 Town, R.M., van Leeuwen, H.P., Blust, R., 2018. Biochemodynamic features of metal ions bound by
751 micro- and nano-plastics in aquatic media. Frontiers in Chemistry doi:10.3389/fchem.2018.00627

752 Turner, A., 2018a. Black plastics: linear and circular economies, hazardous additives and marine
753 pollution. Environment International 117, 308-318.

754 Turner, A., 2018b. Concentrations and migratabilities of hazardous elements in second-hand
755 children's plastic toys. Environmental Science and Technology 52, 3110-3116.

756 Turner, A., 2019. Cadmium pigments in consumer products and their health risks. Science of the
757 Total Environment 657, 1409-1418.

758 Turner, A., Filella, M., 2017. Bromine in plastic consumer products – Evidence for the widespread
759 recycling of electronic waste. Science of the Total Environment 601-602, 374-379.

760 Turner, A., Filella, M., 2020. The influence of additives on the fate of plastics in the marine
761 environment, exemplified with barium sulphate. Marine Pollution Bulletin 158, 111352.

762 Turner, A., Filella, M., 2021. Lead in plastics – recycling of legacy material and appropriateness of
763 current regulations. Journal of Hazardous Materials 404, 124131.

764 Turner, A., Solman, K.R., 2016. Analysis of the elemental composition of marine litter by field-
765 portable-XRF. Talanta 159, 262-271.

766 Turner, A., Wallerstein, C., Arnold, R., 2019. Identification, origin and characteristics of bio-bead
767 microplastics from beaches in **Western Europe**. Science of the Total Environment 664, 938-947.

768 University of Hertfordshire, 2020. PDDP: Pesticide Properties DataBase
769 https://sitem.herts.ac.uk/aeru/ppdb/en/Reports/1614.htm#none_ Accessed 8/20.

770 Van Franeker, J.A., Blaize, C., Danielsen J., et al., 2011. Monitoring plastic ingestion by the northern
771 fulmar *Fulmarus glacialis* in the North Sea. Environmental Pollution 159, 2609–2615.

772 van Putten, E.M., 2011. Heavy metals in food packaging : A literature review. RIVM Report
773 609021114/2011. National Institute for Public Health and the Environment.

774 Vedolin, M.C., Teophilo, C.Y.S., Turra, A., Figueira, R.C.L., 2018. Spatial variability in the
775 concentrations of metals in beached microplastics. Marine Pollution Bulletin 129, 487-493.

776 Viczek, S. A., Aldrian, A., Pomberger, R., Sarc, R., 2020. Origins and carriers of Sb, As, Cd, Cl, Cr, Co,
777 Pb, Hg, and Ni in mixed solid waste – A literature-based evaluation. Waste Management 103, 87-
778 112.

779 VinylPlus, 2014. The European PVC industry's experience in replacing lead and cadmium-based
780 stabilisers. [https://www.stabilisers.eu/wp-content/uploads/2015/11/VinylPlus_Contribution-](https://www.stabilisers.eu/wp-content/uploads/2015/11/VinylPlus_Contribution-Cefic_Eu-Industry.pdf)
781 [Cefic_Eu-Industry.pdf](https://www.stabilisers.eu/wp-content/uploads/2015/11/VinylPlus_Contribution-Cefic_Eu-Industry.pdf). Accessed 8/20.

782 Wagner, S., Schlummer, M., 2020. Legacy additives in a circular economy of plastics: Current
783 dilemma, policy analysis, and emerging countermeasures. *Resources, Conservation & Recycling* 158,
784 104800.

785 Wang, F.Y., Yang, W.W., Cheng, P., Zhang, S.Q., Zhang, S.W., Jiao, W.T., Sun, Y.H., 2019. Adsorption
786 characteristics of cadmium onto microplastics from aqueous solutions. *Chemosphere* 235, 1073-
787 1080.

788 Wilson, D.C., Young, P.J., Hudson, B.C., Baldwin, G., 1982. Leaching of cadmium from pigmented
789 plastics in a landfill site. *Environmental Science and Technology* 16, 560-571.

790 Yu, H., Hou, J.H., Dang, Q.L., Cui, D.Y., Xi, B.D., Tan, W.B., 2020. Decrease in bioavailability of soil
791 heavy metals caused by the presence of microplastics varies across aggregate levels. *Journal of*
792 *Hazardous Materials* 395, 122690.

793 Zhang, H., Wang, J., Zhou, B., Zhou, Y., Dai, Z., Zhou, Q., Christie, P., Luo, Y., 2018. Enhanced
794 adsorption of oxytetracycline to weathered microplastic polystyrene: Kinetics, isotherms and
795 influencing factors. *Environmental Pollution* 243, 1550-1557.

796 Zhang, Z., Chen, Y., 2020. Effects of microplastics on wastewater and sewage sludge treatment and
797 their removal: A review. *Chemical Engineering Journal* 382, 122955.

798 Zhong, H., Wang, W.-X., 2006. Sediment-bound inorganic Hg extraction mechanisms in the gut fluids
799 of marine deposit feeders. *Environmental Science and Technology* 40, 6181-6186.

800 Zitko, V., 1999. Qualitative determination of 10,10'-oxybisphenoxarsine and decabromodiphenyl
801 ether in plastics. *Chemosphere* 38, 629-632.

802

803

Tables

Table 1: Metals in plastics that are regulated in Europe and current limit values according to various directives. TS = migration limits in 0.07 M HCl specified by the Toy Safety Directive; RoHS, ELV, PPW, CFS and OTC = total concentrations specified by directives relating to the Restriction of Hazardous Substances, End-of-Life Vehicles, Packaging and Packaging Waste, contact with foodstuffs and organotin compounds, respectively; hazardous classification is based on inclusion in at least two directives and defined in REACH as a SVHC.

Metal	TS mg kg ⁻¹ (0.07M HCl)	RoHS mg kg ⁻¹ (total)	ELV mg kg ⁻¹ (total)	PPW mg kg ⁻¹ (total)	CFS mg kg ⁻¹ (total)	OTC mg kg ⁻¹ (total)	hazardous
Al	70,000						
As	47				1		yes
Ba	18,750						
Cd	17	100	100	100 ^a			yes
Cr(III)	460						
Cr(IV)	0.2	1000	1000	100 ^a	1 ^b		yes
Co	130						yes
Cu	7700				5		
Hg	160	1000	1000	100 ^a			yes
Mn	15,400						
Ni	930						
Pb	23	1000	1000	100 ^a	2		yes
Sb	560						
Se	460						
Sn	180,000						
Sn (organic)	12					1000	yes
Sr	56,000						
Zn	46,000				100		

^aThe combined limit for all four metals is 100 mg kg⁻¹.

^bThe oxidation state of Cr is not specified but assumed to be VI.

817 Table 2: Examples of hazardous metal-based compounds that have been commonly employed in plastics, and in particular in Europe, along with their
818 physico-chemical properties; nd = no data found. Sources of information: ChemicalBook CAS DataBase; ECHA (2009; 2010; 2011; 2012; 2016; 2017); Filella
819 and Turner (2018); Hansen et al. (2013); Haynes (2015); Lofrano et al. (2018); Malik and Jain (1969); Piver (1973); Ranta-Korpi et al. (2014); RPA (2005);
820 Zitko, 1999). PE = polyethylene; PET = polyethylene terephthalate; PP = polypropylene; PU = polyurethane; PVC = polyvinyl chloride.

metal	compound	chemical formula	description	molecular mass	aq. solubility @ 20°C, mg L ⁻¹	density, g mL ⁻¹	plastic types	function	conc. in plastic, mg kg ⁻¹
As	10,10'-oxybisphenoxarsine	C ₂₄ H ₁₆ As ₂ O ₃	organometallic liquid	502.23	5.0	1.40-1.42	PVC	bacterioside/fungicide	300-500
Cd	cadmium sulphide	CdS	inorganic solid	144.48	1.3	4.83	all	pigment (yellow)	100-25,000
	cadmium selenide	CdSe	inorganic solid	191.38	"insoluble"	5.82	all	pigment (red)	100-25,000
	cadmium stearate	C ₃₆ H ₇₀ CdO ₄	organic acid salt	679.40	"insoluble"	1.28	PVC	stabiliser	1000
	cadmium dodecanoate	C ₂₄ H ₄₆ CdO ₄	organic acid salt	511.04	"insoluble"	nd	PVC	stabiliser	1000
Co	cobalt(II) diacetate	C ₄ H ₆ CoO ₄	organic acid salt	177.02	"readily soluble"	1.71	PET	pigment (blue)	<10,000
Cr(VI)	chromium(VI) trioxide	CrO ₃	inorganic solid	99.99	"soluble"	2.70	PE	catalyst	<5
Hg	<i>see also lead chromate</i>								
	phenylmercury compounds	C _x H _y Hg ₂ O ₄ or C _x H _y HgO ₂	organometallic solids	336.75-837.80	0.14-1843	nd	PU	catalyst	1000-3000
Pb	mercury sulphide	HgS	inorganic solid	232.66	"insoluble"	8.10	PE, PP	pigment (red)	<1000
	lead chromate	PbCrO ₄	inorganic solid	323.19	0.2	6.12	all	pigment (yellow)	<50,000
	lead sulfate	PbSO ₄	inorganic solid	303.26	44.5	6.29	all	pigment (red)	<50,000
	lead molybdate	PbMoO ₄	inorganic solid	367.13	0.16	6.92	all	pigment (red)	<50,000
	tetralead trioxide sulfate	3PbO·PbSO ₄	inorganic solid	972.86	"insoluble"	6.40	PVC	stabiliser	25,000
	trilead bis(carbonate) dihydroxide	Pb ₃ (CO ₃) ₂ (OH) ₂	inorganic solid	775.90	"insoluble"	6.14	PVC	stabiliser	25,000
	trilead dioxide phosphonate	PbHPO ₃ ·2(PbO)	inorganic solid	733.58	"insoluble"	6.90	PVC	stabiliser	25,000
Sn	dibutyltin dilaureate	C ₃₂ H ₆₄ O ₄ Sn	organometallic liquid	631.56	<1.43	1.07	PVC and PU	stabiliser and catalyst	500-3000
	dibutyltin maleate	C ₁₂ H ₂₀ O ₄ Sn	organometallic liquid	346.99	"immiscible"	1.32	PVC	stabiliser	10-10,000

Table 3: Maximum concentrations of Cd and Pb reported in plastic litter from various environments, along with the polymer in which maximum concentrations were observed (PE = polyethylene, PP = polypropylene; PVC = polyvinyl chloride).

location	litter type (no. samples)	Cd, mg kg ⁻¹	Pb, mg kg ⁻¹	polymer	source
Lake Geneva	beached plastic litter (<i>n</i> = 670)	6760	23,500	PE, PVC	Filella and Turner (2018)
North Atlantic subtropical Gyre	mesoplastics (<i>n</i> = 13)	4280	8310	PE	Prunier et al. (2019)
	microplastics (<i>n</i> = 4)	105	112	PE	
NW Europe	water treatment beads (<i>n</i> = 537)	312	5380	PE	Turner et al. (2019)
Ookushi beach, Japan	fishing floats (<i>n</i> = 17)	nd ^a	21,900 ^b	PVC	Nakashami et al. (2012b)
SW England	beached microplastic pellets (<i>n</i> = 752)	3390	5330	PP, PE	Massos and Turner (2017)
	beached microplastic fragments (<i>n</i> = 172)	2620	4820	PP, PE	

^aNot detected

^bConcentration represents the sum of the mean and error provided.

831 Table 4: Concentrations of Cd and Pb acquired by various environmental plastics from their
832 surroundings and evaluated by acid extraction.

location	description	measure	Cd, mg kg ⁻¹	Pb, mg kg ⁻¹	source
Australian coast	beached microplastics	max	0.088	0.50	Carbery et al. (2020)
Azores, N Atlantic	beached microplastics	mean	5.8	4.3	Martins et al. (2020)
Chao Phraya River, Thailand	sediment microplastics	mean		17.6	Ta and Babel (2020)
Chennai coast, India	beached plastics	max		1.85	Suman et al. (2020)
Hong Kong coast	beached microplastics	median	0.04		Li et al. (2020)
Musi River, Indonesia	suspended microplastics	mean		0.47	Purwiyanto et al. (2020)
Nigerian coast	beached microplastics	max	0.10	2.51	Fred-Ahmadu et al. (2020a)
SW English coast	beached pellets	max	0.01	1.08	Ashton et al. (2010)
833 Vis Island, Croatia	beached pellets	max	0.005	8.5	Jasna et al. (2019)

834

835

Figure legends

Figure 1: Energy-dispersive XRF spectra, as counts per second versus energy in keV, of different environmental plastics (of ~ 2 to 8 cm in length) containing hazardous metal-based additives (unpublished data of the authors derived from direct sample analysis using a Niton XLt3+ portable XRF). (a) An irregular fragment of plastic from a beach in SW England pigmented with Cd_2SSe , (b) a piece of wrapping from agricultural land in central Spain pigmented with PbCrO_4 , (c) PVC-film from a beach on Lake Geneva with a Sn-based stabilizer and (d) a curved PVC fragment from a beach in Lake Geneva with a Pb-based stabilizer.

Figure 2: Mobilization of (a) Cd from 100 mg L^{-1} of micronized ($< 1 \text{ mm}$ in two dimensions) polyvinyl chloride (PVC) and (b) Pb from 100 mg L^{-1} of micronized polycarbonate-acryl nitro butadiene (PC-ABS) into different solutions mimicking the digestive environments of a seabird (replotted from Smith and Turner, 2020). The red dashed lines denote the respective Toy Safety Directive migration limits.